

# DATA SHEET



## Finkl Steel

### MPX® HIGH QUALITY PREHARDENED ALLOY STEEL

#### TYPICAL APPLICATIONS

- Mud pump fluid end blocks
- Ancillary oil & gas components
- Alternative to 4130

#### GENERAL

##### Delivery Condition:

Hardened and Tempered, EFVD

**MPX®** is a Cr-Ni-Mo alloy steel that was specifically engineered to increase through-hardenability and eliminate the need for pre-heat treat machining. **MPX®** simplifies the production process and lowers manufacturing costs without compromising quality and performance.

The balanced chemistry and through-hardenability of **MPX®** together with Finkl's industry leading forging practices achieve the optimal combination of strength and toughness through large cross sections. These characteristics allow **MPX®** to be heat treated as a forged bar that can be readily cut and machined directly into finished parts.

**MPX®** creates value by lowering costs, increasing efficiency, and shortening production lead-times.

Finkl Steel Houston stocks **MPX®** in a variety of sizes that are available for immediate shipment.

Note: Provided technical data and information in this data sheet are typical values. Normal variations in chemistry, size and conditions of heat treatment may cause deviations from these values. We suggest that information be verified at time of enquiry or order. For additional data or metallurgical assistance, please contact us.

#### Typical Chemical Analysis\* - % weight

C	Mn	Si	Cr	Ni	Mo
0.32	1.30	0.30	1.90	0.60	0.45

\*Patent pending

#### Tensile Properties

Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation %	Reduction of Area %	Hardness HBW
125 (860)	100 (690)	15	40	255-321

#### Impact Properties

Charpy V-notch Impact Strength at -4 °F (-20 °C)	
Longitudinal Ft-Lb (J)	Transverse Ft-Lb (J)
35 (47)	25 (34)

Reported properties are typical values for a full-size 24" x 24" (0.6m x 0.6m) prehardened bar tested at quarter thickness and width. Other ranges are available.

#### KEY CHARACTERISTICS

- Water quenched and fully tempered
- High through-hardenability
- Excellent low-temperature fracture toughness over a wide range of available strengths
- Fully martensitic, fine grain microstructure
- Low sulfur and phosphorous content and superior microcleanliness
- 100% ultrasonically inspected and certified defect free

#### Finkl Steel—Chicago

1355 E. 93rd Street  
Chicago, IL 60619  
773.975.2510  
TOLL-FREE: 800.621.1460

#### Finkl Steel—Houston

14710 Cypress North Houston Rd.  
Cypress, TX 77429  
281-640-2050

[www.finkl.com](http://www.finkl.com)